

### Removal of Adhesive/Mastic/Silicone

**Purpose:** To remove adhesive, tile mastic or silicone from tile or stone surfaces.

#### Method

**Product:** Aqua Mix **Sealer & Coating Remover** (Notes A & B).

**Equipment:** **AquaBug Cleaning Kit**, scrub brush or nylon scrub pad, scraper and white cotton towels.

**Coverage:** Approximately 7 m<sup>2</sup> – 10 m<sup>2</sup> per 3.785 L.

- Procedure:**
1. Always test a small area first to ensure satisfactory results.
  2. Sweep or vacuum surface.
  3. Apply Aqua Mix **Sealer & Coating Remover** to a small manageable area up to 2.5 m<sup>2</sup>
  4. Allow to dwell up to 2 hours without drying or until coating or residue softens. (Adding Aqua Mix **Poultice** to standing solution just before scrubbing will enhance cleaning procedure).
  5. Agitate with **AquaBug Cleaning Kit**, scrub brush or nylon scrub pad. A scraper may be used for removal of thick residue.
  6. If necessary, apply additional remover or sprinkle with hot water and agitate with a scrub brush.
  7. Remove residue and wipe surface dry using clean, absorbent white cotton towels.
  8. Rinse thoroughly with clean water.
  9. Repeat procedure if necessary.

**Note A:** Do not use on synthetic agglomerate or other resinous surfaces.

**Note B:** Aqua Mix **Sealer & Coating Remover** will remove sealers and wax-type coatings.

#### Technical Assistance:

1. Call +61 2 9521 4000
2. Visit our web site [www.aquamix.com.au](http://www.aquamix.com.au)
3. Email all technical questions to [technical@aquamix.com.au](mailto:technical@aquamix.com.au)

This recommendation is intended as a general guideline for the removal of adhesive/mastic/silicone. The actual removal requirements may vary depending on the method of application, temperature, and amount of adhesive/mastic to be removed.

**Read product directions thoroughly prior to use.**

**Always test first. Keep surface clean and dry to reduce possibility of slip-fall accidents.**